
UNITED “PREMIUM WHITE” ALLOY # 907

Thank you for using UNITED’S alloys.

UNITED’S # 907 ALLOY may be used for **14 K – 18 K white gold casting**, which produces a **Premium White finished color**. # 907 contains a boron deoxidizer.

You should obtain excellent results by following a few simple instructions.

MELTING

We do recommend pre-alloying all alloy and fine gold with aggressive stirring & fluxing to assure a uniform mixture.

Step : 1	Pre- Alloying (Fine gold + alloy) Temperature	1080° - 1090° C 1976° - 1994° F
Step : 2	Casting Temperature for 14 K – 18 K Alloyed Grain	1040° - 1050° C 1904° - 1922° F

NOTES: Melt temperature may vary with type of unit. This alloy is designed for casting only.

FLASK TEMPERATURE

Normal recommended temperature in the range of **580° C to 700° C / 1076° F – 1292° F** depending on size of flask, karat & type of jewelry.

FLUXING

Fluxing white gold is extremely important to pick-up oxides. Boric Acid is the recommended flux. Do not use carbon fluxes or any fluxes designed for refining; i.e., soda ash, saltpeter, etc. Avoid flux in bottom pour automatic casting units.

QUENCH TIME

8 – 10 minutes.

INVESTMENT REMOVAL

Most standard investment removers will successfully remove the investment powder. Fluoric-based investment removers are the best for removing the silicon oxide invisible coating. Use of aggressive acids causes stress corrosion and surface damage and is therefore not recommended.

UNITED’S Brite-Cast™ Investment Remover works effectively in removing fire scale as well as preventing stress corrosion or surface damage of the cast piece.

REMELTING

We recommend a 70% fresh - 30% scrap mix. White gold alloy has about 1/3 the reusability of yellow gold alloys.

TECHNICAL ASSISTANCE

Always available... Call 1-800-999-3463 / 1-800-999-FINE
E-mail / doc@unitedpmr.com Web-Site / www.unitedpmr.com

2781 Townline Road, Alden, NY 14004, USA.
Phone : (800) 999-3463; International Phone : +1-(716)-683-8334
Fax : (800) 533-6657; International Fax : +1-(716)-683-5433
E mail: sales@unitedpmr.com; Website: www.unitedpmr.com